

Chemical Preparation of Iron Oxide Nanoparticles Using Plants Extracts in Antibacterial Application

Wisam Jafer Aziz, Aliyaa Abd Urabe*

Department of Physics, College Science, Mustansiriyah University, Baghdad, Iraq

Email address:

aliyaa.13@umustansiriyah.edu.iq (A. A. Urabe)

*Corresponding author

To cite this article:

Wisam Jafer Aziz, Aliyaa Abd Urabe. Chemical Preparation of Iron Oxide Nanoparticles Using Plants Extracts in Antibacterial Application. *International Journal of Bioorganic Chemistry*. Vol. 4, No. 1, 2019, pp. 1-6. doi: 10.11648/j.ijbc.20190401.11

Received: February 2, 2019; Accepted: March 11, 2019; Published: March 26, 2019

Abstract: In this studying the green synthesis of Iron Oxide nanoparticles (Fe_2O_3 NPs) with Celery stalks and green tea leaves extract were used. The fresh suspension of plant extracts were green- brown in color. However, after acting of FeNO_3 within 20min, the suspension showed the change in color and turned dark brown after 4 hours of incubation at room temperature. Formation of Iron oxide nanoparticles was confirmed using X-ray is spectral analysis and showed the characteristic Bragg peaks of (111) to green tea extract and (111) to celery extract, plant of the face center cubic (FCC) Iron Oxide nanoparticles. The scanning electron microscope (SEM) Iron oxide nanoparticles see small particles and rode. The synthesized Fe_2O_3 NPs colloidal solution has shown better antibacterial activity against both Gram-positive and Gram-negative bacterial strains. The diameters of the inhibition zones of Fe_2O_3 NPs against the bacterial strains were, *S. aureus* (27 mm) p. aeruginos (29mm) with camellia sinensis extract and *S. aureus* (22 mm) p. aeruginos (25mm) with *Apium graveolens* extract at 50 $\mu\text{g}/\text{ml}$ concentration.

Keywords: Synthesis, Iron Oxide Nanoparticles, Camellia Sinensis Leaves (Green Tea), *Apium Graveolens* (Celery), Extract, Antibacterial Activity

1. Introduction

Nanomaterial's molecules in a way that is very necessary and common green synthesis is create environmentally friendly nanomaterial with high specifications Since the plant extract contains various secondary metabolites, it acts as the reducing and stabilizing agent for the bioreduction reaction to synthesize the optimum nanoparticles properties [1]. This approach has been actively used in recent years as an alternative, efficient, inexpensive, and environmentally safe method for producing nanoparticles with specific properties [2]. Chemical methods involve the reduction of chemicals phytochemicals [3], electrochemical procedures [4] microemulsion, chemical precipitation, chemical vapor condensation, pulse electrode position [5]. A typical procedure involves growing nanoparticles in a liquid medium containing various reactants, in particular reducing agents, such as sodium borohydride or potassium bitartrate [6] or methyl polyethylene glycol [7] or hydrazine [8]. A nanometer (nm) is a billionth of a meter, 10^{-9} . The bacterial membrane

contains sulfur-containing proteins, and the Iron oxide nanoparticles interact with these proteins in the cell as well as with the phosphorus-containing compounds like DNA. The nanoparticles release Iron oxide in the bacterial cells enhancing their bactericidal activity [9]. The present review focuses on the synthesis of Fe_2O_3 NPs with particular emphasis on biological synthesis using plant extracts and most commonly proposed mechanisms regarding the antibacterial properties of nanoparticles [10].

2. Material and Methods

2.1. Chemical and Reagents

In this study, has been used Iron nitrate hexhydrate ($\text{Fe}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$), (99%), (Reagent World, USA, purity 99.99%), Sodium hydroxide, Celery stalks and green tea leaves buds were collected from the local market. Distill water (DW) was used as a solvent.

2.2. Preparation of Green Reducing and Stabilizing Agent

The Celery stalks (*Apium graveolens*) and green tea leaves (*camellia sinensis*) were collected from the local market, (Baghdad). The plants have been catted into small pieces and washed with distil water to remove impurities *Apium graveolens* (30g) and 200 mL (DW) were homogenized at 80°C in continuous stirring, in cooled down and filtered. The filtrate (brown color) was collected and used for the synthesis of Iron oxide nanoparticles, the same procedure was don for green tea leaves.

2.3. Synthesis of Iron-Oxide Nanoparticles

To synthesis the Iron oxide nanoparticles, freshly extract

(30 mL) was added to 0.02 M solution of Iron nitrate hexahydrate, heated at 75°C till precipitates appeared and then temperature reduced to 60°C and kept the solution at for 60 min. The mixture was kept overnight at room temperature and then centrifuged at 14000 rpm for 10 min. The precipitates were washed this with ultrapure water and absolute ethanol to remove unreacted particles and impurities. The obtained precipitates were dried in an furnace at 500°C for 2h, grinded and subjected to characterization, Synthesis of Iron oxide nanoparticles using plant extracts and mixing it with Iron nitrate and turning it from pink to gray forming the Iron oxide. The process to synthesis of Fe₂O₃ NPs with plants is show in figure 1.




Figure 1. Synthesis of Iron oxide nanoparticles using plant extracts *Camellia* and *Apium* with Iron nitrate.

3. Results and Discussion

3.1. X-Ray Analysis

Reveal XRD of Iron oxide nanoparticles using green tea and celery extracts. Such as Bragg diffraction values are (002, 200, 140, 110, 111, 006, 130, 023, 132, 004, 214, 200) of Iron oxide nanoparticles with *camellia sinensis* extract. XRD pattern in Figure 3 show the Iron oxide nanoparticles formed with crystalline in nature with a mixed phase structure (Rhombohedral) in peaks (002, 111, 220, 020, 200, 100, 220, 411, 322, 004, 315, 424, 505, 312) celery extract, XRD pattern indicates that the Iron oxide nanoparticles formed are crystalline in nature with a mixed phase structure (Orthorhombic). The average crystallite size of the Iron oxide nanoparticles was calculated, using Debye-Scherrer equation):

$$D = \frac{k\lambda}{\beta \cos\theta} \quad (1)$$

Where: D is the particle size (nm), k is a constant equal to 0.94, λ is the wavelength of X-ray radiation (1.541Å), β is the full-width at half maximum (FWHM) of the peak (in radians) and 2 theta is the Bragg angle (in degrees). The average crystallite size was found to be in the range of (23-43 nm) from *Camellia sinensis* extract and (20-99 nm) from *Apium graveolens* extract.




Figure 2. XRD pattern of Iron oxide nanoparticles using *Camellia sinensis* extract.




Figure 3. XRD pattern of Iron oxide nanoparticles using *Apium graveolens* extract.

3.2. FE-SEM Analysis

The FE-SEM images of Iron Oxide nanoparticles are shown in Figure 4. The morphology of the nanoparticles indicates irregular, cubic and hexagonal shapes of various sizes that are agglomerated. Further observations with higher

magnifications reveal these images possess smooth surfaces. At much higher magnification the images are seen as large particles which can be attributed to aggregation or clustering of smaller particles.




Figure 4. FE-SEM of Iron oxide nanoparticles preparing using *Camellia sinensis* extract.




Figure 5. FE-SEM of Iron oxide nanoparticles preparing using *Apium graveolens* extract.

3.3. UV-Visible Spectroscopy

The formation of Iron nanoparticles was first confirmed based on a change in color of the reaction mixture at room temperature from light brown to dark brown within 15 min. This was followed by UV-vis spectroscopy which is frequently used to characterize synthesized metal nanoparticles. Figure 6 shows the UV-vis absorption

spectrum of the synthesized Iron nanoparticles. The maximum absorption peaks are (220 nm) for camellia sinensi and (225 nm) for Apium graveolens, The energy band gaps are (2.9 eV) of camellia sinensi extract and (4.01 eV) of Apium graveolens extract as a result of quantum confinement and small molecules as shown in Figure 7.




Figure 6. UV-Vis absorption spectra of Iron oxide NPs with *Camellia sinensis* extract and *Apium graveolens* extract.




Figure 7. The energy band gap of Iron oxide Nanoparticles with *Camellia sinensis* extract and *Apium graveolens* extract.

3.4. Antibacterial Susceptibility Assay

The inhibition zone of Iron oxide nanoparticles biofabricated from the *Apium graveolens* and *camellia sinensis* extracts against two pathogens is shown in Figure 8, Table 1. And Both each of Gram-negative (*p. aeruginosa*) and Gram-positive (*S. aureus*) bacteria organisms were used in this study. Human pathogens capable of causing diseases ranging from skin infections, pneumonia, sepsis, toxic shock syndrome, urinary tract infections, vomiting, anaemia, kidney infections, osteomyelitis, septicemia, lung infection to wound infections. The surfaces of the Iron oxide nanoparticles might have interacted directly with the bacterial outer membrane, causing the membrane to rupture thereby killing the organism. So, the antibacterial activity exhibited by the Iron

nanoparticles here is attributed to their small size and high surface to volume ratio, which allows them to interact closely with microbial membranes. Result was used as a positive control in the experiment. The minimum inhibitory concentration (MIC) of the Iron oxide nanoparticles, Note that the presence of plant extracts increase the effectiveness of material nanoparticles as green tea extract increase the proportion of negative bacteria killing of 20 mm with celery extract and 18 mm without the extract to 31 mm with leaves extract and the presence of plant extracts increase the effectiveness of oxide nanoparticles as green tea extract increase the proportion of positive bacteria killing of 18 mm with celery extract and 17 mm without the extract to 25 mm with leaves extract.




Figure 8. Rate of inhibition for bacteria *Pseudomonas a eruginosa* a) *S. aureus* b) *P. aeruginosa* for Iron oxide NPs of plant extracts.

Table 1. Zone Inhibition (mm) of Iron oxide NPs against pathogens.

Type of material nanoparticles used	Zone of inhibition (mm) at 200µg/ml concentration <i>S. aureus</i>	Zone of inhibition (mm) at 200µg/ml concentration <i>P. aeruginosa</i>	Percentage of Inhibition (%) <i>S. aureus</i>	Percentage of Inhibition (%) <i>P. aeruginosa</i>
Fe ₂ O ₃ NPs pure	17	18	18.8	20
Fe ₂ O ₃ with <i>Apium graveolens</i>	18	20	20	22.2
Fe ₂ O ₃ with <i>Camellia sinensis</i> leaves	25	31	27.8	34.4

4. Conclusions

Iron oxide nanoparticles were synthesized using *Camellia sinensis* leaves and *Apium graveolens* extracts as a green method of nanoparticles synthesis that does not introduce harmful substances into the environment and ensures cost effectiveness. The particle size has been calculated to be in the range (20–99 nm). These Iron oxide nanoparticles inhibited the growth of *S. aureus*, *P. aeruginosa*. Therefore, it is pertinent to conclude that the Iron oxide nanoparticles could be used in the treatment of diseases and infections caused by these organisms. The best results were obtained from chemical preparation simple and clear differentiation peaks of Fe₂O₃ NPs with green tea and best to inhibition the existence of green tea extract was (25-31mm) of *S. aureus* and *P. aeruginosa* bacteria respectively.

References

- [1] Abou El-Nour KMM, Eftaiha Aa, Al-Warthan A, Ammar RAA. Synthesis and applications of silver nanoparticles. *Arabian Journal of Chemistry*. 2010; 3 (3): 135-40.
- [2] Mohanpuria P, Rana NK, Yadav SK. Biosynthesis of nanoparticles: technological concepts and future applications. *Journal of Nanoparticle Research*. 2007; 10 (3): 507-17.
- [3] Padil V. V. T. and Černík M. (2013). Green synthesis of copper oxide nanoparticles using gum karaya as a biotemplate and their antibacterial application. *Int. J. Nanomed.*, 8, 889-898.
- [4] Hoseyni S. J., Manoochehri M. and Asli M. D. Synthesis of cobalt nanoparticles by complex demolition method using the reaction between organic ligand Schiff base and cobalt chloride by ultrasonication. *Bulletin de la Société Royale des Sciences de Liège*, (2017). 86, 325-331.
- [5] Koyyati R., Kudle K. R. and Padigya P. R. M. Evaluation of antibacterial and cytotoxic activity of green synthesized cobalt nanoparticles using *Raphanus sativus* var. *longipinnatus* leaf extract. *Int. J. PharmTech Res* (2016,.) 472-466 (3) 9.
- [6] A. Phukan, R. P. Bhattacharjee, D. K. Dutta, Stabilization of SnO₂ nanoparticles into the nanopores of modified Montmorillonite and their antibacterial activity, *Adv. Powder Technol.* 28 (1) (2017) 139–145.
- [7] C. Ragupathi, L. John, Kennedy, J. Judith Vijaya, A new approach: Synthesis, characterization and optical studies of nano-zinc aluminate, *Adv. Powder Technol.* 25 (2014) 267–273.
- [8] A. B. Samui, D. S. Patil, C. D. Prasad, N. M. Gokhale, Synthesis of nanocrystalline 8YSZ powder for sintering SOFC material using green solvents and dendrimer route, *Adv. Powder Technol.* 27 (5) (2016) 1879–1884.
- [9] M. Sundrarajan, S. Ambika, K. Bharathi, Plant-extract mediated synthesis of ZnO nanoparticles using *Pongamia pinnata* and their activity against pathogenic bacteria, *Adv. Powder Technol.* 26 (2015) 1294–1299.
- [10] P. Raveendran, J. Fu, S. L. Wallen, Completely “green” synthesis and stabilization of metal nanoparticles, *J. Am. Chem. Soc.* 125 (2003) 13940–13941.
- [11] R. S. Patil, M. R. Kokate, S. S. Kolekar, Bioinspired synthesis of highly stabilized silver nanoparticles using *Ocimum tenuiflorum* leaf extract and their antibacterial activity, *Spectrochim. Acta A Mol. Biomol. Spectrosc.* 91 (2012) 234–238.
- [12] M. Fazlzadeh, K. Rahmani, A. Zarei, H. Abdoallahzadeh, F. Nasiri, R. Khosravi, A novel green synthesis of zero valent iron nanoparticles (NZVI) using three plant extracts and their efficient application for removal of Cr (VI) from aqueous solutions, *Adv. Powder Technol.* 28 (2017) 122–130.
- [13] J. K. Patra, Y. Kwon, K. -H. Baek, Green biosynthesis of gold nanoparticles by onion peel extract: Synthesis, characterization and biological activities, *Adv. Powder Technol.* 27 (2016) 2204–2213.
- [14] A. Phukan, R. P. Bhattacharjee, D. K. Dutta, Stabilization of SnO₂ nanoparticles into the nanopores of modified Montmorillonite and their antibacterial activity, *Adv. Powder Technol.* 28 (2017) 139–145.
- [15] B. Siripireddy, B. K. Mandal, Facile green synthesis of zinc oxide nanoparticles by *Eucalyptus globulus* and their photocatalytic and antioxidant activity, *Adv. Powder Technol.* 28 (2017) 785–797.
- [16] Wisam J. Aziz and Haneen A. Jassim, A NEW PARADIGM SHIFT TO PREPARE COPPER NANOPARTICLES USING BIOLOGICAL SYNTHESIS AND EVALUATION OF ANTIMICROBIAL ACTIVITY, *Plant Archives* Vol. 18 No. 2, 2018 pp. 2020-2024 e- ISSN: 2581-6063 (online), ISSN: 0972-5210.
- [17] S. F. Hasany, I. Ahmed, Rajan J, A. Rehman, Systematic Review of the Preparation Techniques of Iron Oxide Magnetic Nanoparticles, *Nanoscience and Nanotechnology* 2012, 2 (6): 148-158, DOI: 10. 5923/j. nn. 20120206. 01, (2012).
- [18] Olanrewaju Sam Olayeriju, Mary Tolulope Olaleye, Olamide Olajusi Crown, Kayode Komolafe, Aline Augusti Boligon, Margareth Linde Athayde and Akintunde Afolabi Akindahunsi, Ethylacetate extract of red onion (*Allium cepa* L.) tunic affects hemodynamic parameters in rats, *Food Science and Human Wellness* 4 -115–122 (2015).
- [19] Wei Wu Æ Quanguo He Æ Changzhong Jiang, Magnetic Iron Oxide Nanoparticles: Synthesis and Surface Functionalization Strategies, *Nanoscale Res Lett* 3: 397–415, DOI 10. 1007/s11671-008-9174-9. 314 (2006) 964-967 (2008).

- [20] Ngo Ngoc Trung, Nguyen Thi Tho, Bui Thi Thuy Dung, Hoang Thi My Nhung, Nguyen Dinh Thang, Effects of ricin extracted from seeds of the castor bean (*ricinu communis*) on cytotoxicity and tumorigenesis of melanoma cells, *Biomedical Research and Therapy*, 3 (5): 633-644, DOI 10. 7603/s40730-016-0023-7, ISSN 2198-4093, (2016).
- [21] A. A. Haleemkhan, Naseem, B. Vidya Vardhini, Synthesis of Nanoparticles from Plant Extracts, *International Journal of Modern Chemistry and Applied Science* 2015, 2 (3), 195-203.
- [22] S. Kanagasubbulakshmi and K. Kadirvelu, Green Synthesis of Iron Oxide Nanoparticles using *Lagenaria Siceraria* and Evaluation of its Antimicrobial Activity, *Defence Life Science Journal*, Vol. 2, No. 4, October 2017, pp. 422-427, DOI: 10. 14429/dlsj. 2. 12277. 2017, DESIDOC.
- [23] Mandeep Kaur and Dimple Sethi Chopra, Green Synthesis of Iron Nanoparticles for Biomedical Applications, *Glob J Nanomed*, Review Article, Volume 4 Issue 4 - October 2018, DOI: 10. 19080/GJN. 2018. 04. 555643.
- [24] Valentin V. Makarov, Svetlana S. Makarova, Andrew J. Love, Olga V. Sinitsyna, Anna O. Dudnik, Igor V. Yaminsky, Michael E. Taliansky, and Natalia O. Kalinina, Biosynthesis of Stable Iron Oxide Nanoparticles in Aqueous Extracts of *Hordeum vulgare* and *Rumex acetosa* Plants, *Langmuir*, dx.doi.org/10. 1021/la5011924, Received: March 28, (2014).
- [25] Vinicius Ramos, DeJane Alves, Mariana Braga, Geraldo Carvalho, and Custódio Santos, Extraction and isolation of anti-tryptic castor-bean (*Ricinus communis* L.) substances and their effects on *Spodoptera frugiperda* (Smith, 1797) (Lepidoptera: Noctuidae), 128 *CHILEAN JOURNAL OF AGRICULTURAL RESEARCH* 73 (2) APRIL-JUNE 2013 Extraction and isolation of anti-tryptic castor-bean (*Ricinus communis* L.) substances.
- [26] Siska Siska, Abdul Mun'im, Anton Bahtiar and Franciscus D. Suyatna, Effect of *Apium graveolens* Extract Administration on the Pharmacokinetics of Captopril in the Plasma of Rats, *Sci. Pharm*, doi: 10. 3390/scipharm86010006, 2018, 86, 6.
- [27] Mona. H. Ibrahim, A. A. Ibrahiem and T. R. Dallou, BIOSYNTHESIS OF SILVER NANOPARTICLES USING POMEGRANATE JUICE EXTRACT AND ITS ANTIBACTERIAL ACTIVITY, *International Journal of Applied Sciences and Biotechnology (IJASBT)*, (2016) *Int J Appl Sci Biotechnol*, Vol 4 (3): 254-258.
- [28] Alaa Alhazmi, *Pseudomonas aeruginosa* – Pathogenesis and Pathogenic Mechanisms, *International Journal of Biology*; Vol. 7, No. 2; 2015, ISSN 1916-9671 E-ISSN 1916-968X Published by Canadian Center of Science and Education.